



Soundness of Aggregates Test Results
NYSDOT Method, Magnesium Sulfate, 10 Cycles

Product: Washed NYSDOT #2 Stone
Source: West of Jeddo Creek-working 30' face
Plant: 72" & 66" Spokane's Running
Client: Shelby Crushed Stone, Inc.

Project No: 10-028
Lab ID: 10-380
Date: 08/19/10

Sieve Size Range	Grading of Original Sample %	Weight of Test Fractions Before Test g	% Passing Designated Sieve After Test	Weighted Percentage Loss %
2"-1"	0.5	0.0	NA	NA
1"-1/2"	98.1	616.2	12.2	12.0
1/2"-1/4"	1.1	0.0	NA	NA
1/4"-#10	0	0.0	NA	NA
Totals	99.7			12.0

Submitted by: Jeanne M. Asquith

Date: 8/19/2010