



ATLANTIC TESTING LABORATORIES

Albany
22 Corporate Drive
Clifton Park, NY 12065
518-383-9144 (T)
518-383-9166 (F)

TRANSMITTAL

April 27, 2012

Shelby Crushed Stone, Inc.
10830 Blair Road
Medina, New York 14103

Attn: Mr. Tom Biamonte

E/Mail: tom@shelbystone.com

Re: Laboratory Analysis
Aggregate Testing
Core Samples
ATL Project No. AT1069

Dear Mr. Biamonte:

On March 15, 2012, your representative delivered two core samples (ATL Sample nos. AT1069S16 and AT1069S17) from Shelby Crushed Stone, to our Clifton Park, New York, facility for testing. After the samples were crushed and sized a 10-cycle Magnesium Sulfate Test, in accordance with NYSDOT 703-07 P,G, was performed. The laboratory test results follow:

10-CYCLE MAGNESIUM SULFATE SOUNDNESS

NYSDOT 703-07 P,G
MW-1-08, 36.5 – 79.3 ft.

| ATL Sample No. | Sieve Fraction | Initial Weight (g) | Final Weight (g) |
|---------------------------------------|----------------|--------------------|------------------|
| AT1069S16 S-1 | 1" – 3/4" | 1505.2 | 1430.2 |
| | 3/4" – 1/2" | 1008.1 | 919.7 |
| Totals: | | 2513.3 | 2349.9 |
| NYSDOT Specification: < 18% | | Loss: 6.5% | |

10-CYCLE MAGNESIUM SULFATE SOUNDNESS

NYSDOT 703-07 P,G
MW-2-08, 28.3 – 86.3 ft.

| ATL Sample No. | Sieve Fraction | Initial Weight (g) | Final Weight (g) |
|---------------------------------------|----------------|--------------------|------------------|
| AT1069S17 S-2 | 1" – 3/4" | 1507.5 | 1440.1 |
| | 3/4" – 1/2" | 996.7 | 893.9 |
| Totals: | | 2504.2 | 2334.0 |
| NYSDOT Specification: < 18% | | Loss: 6.8% | |